

Nye Lubricants 173 (SO) Synthetic Oil

Category : Fluid , Lubricant , Polyalphaolefin (PAO)

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-173-SO-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	150	150	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	351 cSt	351 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	34.6 cSt	34.6 cSt	Base Oil; ASTM D445
Evaporation Loss	1.0 %	1.0 %	6 hrs, 176C; ASTM D972

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	Recommended
Minimum Service Temperature, Air	-35.0 °C	-31.0 °F	Recommended
Pour Point	-40.0 °C	-40.0 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	PAO	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China