

Nye Lubricants 176A (SO) Synthetic Oil

Category : Fluid , Lubricant , Polyalphaolefin (PAO)

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-176A-SO-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	132	132	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	378 cSt	378 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	38 cSt	38 cSt	Base Oil; ASTM D445
Evaporation Loss	0.47 %	0.47 %	22 hrs, 150C; ASTM D972

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	Recommended
Minimum Service Temperature, Air	-30.0 °C	-22.0 °F	Recommended
Pour Point	-36.0 °C	-32.8 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	PAO	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China