

## Nye Lubricants 179 (SO) Synthetic Oil

Category : Fluid , Lubricant , Polyalphaolefin (PAO)

**Material Notes:**

Information provided by Nye Lubricants.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nye-Lubricants-179-SO-Synthetic-Oil.php](http://www.lookpolymers.com/polymer_Nye-Lubricants-179-SO-Synthetic-Oil.php)

Physical Properties	Metric	English	Comments
Viscosity Measurement	127	127	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	29 cSt	29 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	5.5 cSt	5.5 cSt	Base Oil; ASTM D445
Evaporation Loss	1.4 %	1.4 %	22 hrs, 149C; ASTM D972

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	120 °C	248 °F	Recommended
Minimum Service Temperature, Air	-54.0 °C	-65.2 °F	Recommended
Pour Point	-62.0 °C	-79.6 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	PAO	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China