

## Nye Lubricants 179A (SO) Synthetic Oil

Category : Fluid , Lubricant , Polyalphaolefin (PAO)

**Material Notes:**

Information provided by Nye Lubricants.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nye-Lubricants-179A-SO-Synthetic-Oil.php](http://www.lookpolymers.com/polymer_Nye-Lubricants-179A-SO-Synthetic-Oil.php)

| Physical Properties                  | Metric  | English | Comments                                |
|--------------------------------------|---------|---------|---|
| Viscosity Measurement                | 127     | 127     | Viscosity Index of Base Oil; ASTM D2270 |
| Kinematic Viscosity at 40°C (104°F)  | 29 cSt  | 29 cSt  | Base Oil; ASTM D445                     |
| Kinematic Viscosity at 100°C (212°F) | 5.5 cSt | 5.5 cSt | Base Oil; ASTM D445                     |
| Evaporation Loss                     | 1.4 %   | 1.4 %   | 22 hrs, 149C; ASTM D972                 |

| Thermal Properties               | Metric   | English  | Comments           |
|----------------------------------|----------|----------|--------------------|
| Maximum Service Temperature, Air | 120 °C   | 248 °F   | Recommended        |
| Minimum Service Temperature, Air | -54.0 °C | -65.2 °F | Recommended        |
| Pour Point                       | -62.0 °C | -79.6 °F | Base Oil; ASTM D97 |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Base Fluid Type        | PAO   |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China