

Nye Lubricants 271 (SO) Synthetic Oil

Category : Fluid , Lubricant , Polyalphaolefin (PAO)

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-271-SO-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	148	148	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	73 cSt	73 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	11 cSt	11 cSt	Base Oil; ASTM D445
Evaporation Loss	0.200 % @Temperature 121 °C, Time 86400 sec	0.200 % @Temperature 250 °F, Time 24.0 hour	ASTM D972

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	120 °C	248 °F	Recommended
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	Recommended
Pour Point	-60.0 °C	-76.0 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	PAO/Plybtne	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China