

Nye Lubricants 704C (IG) Synthetic Oil

Category : Fluid , Lubricant , Clay Gellant , Synthetic Ether Base

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-704C-IG-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Kinematic Viscosity at 100°C (212°F)	3.1 cSt	3.1 cSt	Base Oil; ASTM D445
Evaporation Loss	0.50 %	0.50 %	22 hrs, 100C; ASTM D972

Mechanical Properties	Metric	English	Comments
Penetration P(0), 1/10 mm	283	283	ASTM D217
Penetration P(60), 1/10 mm	296	296	ASTM D217
Oil Separation	2.3 %	2.3 %	30 hrs, 100C; FTM 719B, 321.2

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	Recommended
Minimum Service Temperature, Air	-65.0 °C	-85.0 °F	Recommended

Descriptive Properties	Value	Comments
Base Fluid Type	Ester(Di)	
Gellant Type	Clay	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China