

Nye Lubricants 708F (NG) Synthetic Oil

Category : Fluid , Lubricant , Clay Gellant , Polyalphaolefin (PAO)

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-708F-NG-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Kinematic Viscosity at 100°C (212°F)	5.8 cSt	5.8 cSt	Base Oil; ASTM D445
Evaporation Loss	43 %	43 %	22hrs 176C; ASTM D972

Mechanical Properties	Metric	English	Comments
Penetration P(0), 1/10 mm	271	271	ASTM D217
Penetration P(60), 1/10 mm	275	275	ASTM D217
Oil Separation	4.7 %	4.7 %	30 hrs, 176C; FTM 719B, 321.2

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	Recommended
Minimum Service Temperature, Air	-65.0 °C	-85.0 °F	Recommended

Descriptive Properties	Value	Comments
Base Fluid Type	PAO	
Gellant Type	Clay	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China