

## Nye Lubricants 774F (NG) Synthetic Oil

Category : Fluid , Lubricant , Polyalphaolefin (PAO) , Silica Gellant

**Material Notes:**

Information provided by Nye Lubricants.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nye-Lubricants-774F-NG-Synthetic-Oil.php](http://www.lookpolymers.com/polymer_Nye-Lubricants-774F-NG-Synthetic-Oil.php)

Physical Properties	Metric	English	Comments
Viscosity Measurement	280	280	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	5548 cSt	5548 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	525 cSt	525 cSt	Base Oil; ASTM D445
Evaporation Loss	0.10 %	0.10 %	24 hrs, 100C; ASTM D972

Mechanical Properties	Metric	English	Comments
Penetration P(0), 1/10 mm	269	269	ASTM D217
Penetration P(60), 1/10 mm	295	295	ASTM D217
Oil Separation	1.2 %	1.2 %	24 hrs, 100C; FTM 719B, 321.2

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	120 °C	248 °F	Recommended
Minimum Service Temperature, Air	-30.0 °C	-22.0 °F	Recommended
Pour Point	-30.0 °C	-22.0 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	PAO	
Gellant Type	Silica (WL)	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China