

Nye Lubricants 781A (NG) Synthetic Oil

Category : Fluid , Lubricant , Lithium Gellant , Organic Soap Gellant , Silicone Base

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-781A-NG-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	371	371	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	55.4 cSt	55.4 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	19.5 cSt	19.5 cSt	Base Oil; ASTM D445
Evaporation Loss	0.50 %	0.50 %	24 hrs, 100C; ASTM D972

Mechanical Properties	Metric	English	Comments
Oil Separation	5.6 %	5.6 %	24 hrs, 100C; FTM 719B, 321.2

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	Recommended
Minimum Service Temperature, Air	-70.0 °C	-94.0 °F	Recommended
Pour Point	-73.0 °C	-99.4 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	Sil.(Clrphn)	
Gellant Type	Li soap	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China