

Nye Lubricants UniFlor 8130 (475) (UF) Synthetic Oil

Category : Fluid , Lubricant , Perfluoropolyether (PFPE)

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-UniFlor-8130-475-UF-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	119	119	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	60 cSt	60 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	8.7 cSt	8.7 cSt	Base Oil; ASTM D445
Evaporation Loss	0.40 %	0.40 %	24 hrs, 150C; ASTM D972

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	175 °C	347 °F	Recommended
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	Recommended
Pour Point	-54.0 °C	-65.2 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	PFPE(pnd)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China