

Nye Lubricants UniFlor 8971R (898RP-1) (UF) Synthetic Oil

Category : Fluid , Lubricant , Perfluoropolyether (PFPE) , PTFE Gellant

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-UniFlor-8971R-898RP-1-UF-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	320	320	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	90 cSt	90 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	25 cSt	25 cSt	Base Oil; ASTM D445
Evaporation Loss	0.00 %	0.00 %	24 hrs, 100C; ASTM D972

Mechanical Properties	Metric	English	Comments
Penetration P(0), 1/10 mm	288	288	ASTM D217
Penetration P(60), 1/10 mm	277	277	ASTM D217
Oil Separation	5.6 %	5.6 %	24 hrs, 100C; FTM 719B, 321.2

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	225 °C	437 °F	Recommended
Minimum Service Temperature, Air	-75.0 °C	-103 °F	Recommended
Pour Point	-80.0 °C	-112 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	PFPE(lin)	
Gellant Type	PTFE	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China