

Nylene® 406 Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced, Flame Retardant

Material Notes:

Injection molding grade. Dry as molded. Nylene 406 is a general purpose, fast cycling molding resin. Crystallization initiators provide fast molding cycles through rapid melt set-up. Parts molded from 406 have better dimensional stability at moisture equilibrium than parts molded from conventional nylon. ALM, Nylene Canada, and Custom Resins are all operating companies of Polymeric Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nylene-406-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D792
Water Absorption	1.5 %	1.5 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	75.0 MPa	10900 psi	ASTM D638
Elongation at Break	25 %	25 %	ASTM D638
Izod Impact, Notched	0.400 J/cm	0.749 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	182 °C	360 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	71.0 °C	160 °F	ASTM D648
Flammability, UL94	V-2	V-2	

Processing Properties	Metric	English	Comments
Processing Temperature	232 - 243 °C	450 - 469 °F	At Nozzle
Nozzle Temperature	232 - 243 °C	450 - 469 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China