

Nylene® 600 Nylon 6, 50% RH, Extrusion Grade

Category: Polymer, Thermoplastic, Nylon, Nylon 6, Nylon 6, Extruded

Material Notes:

Extrusion grade. Nylene 600 is a general purpose, medium viscosity, extrusion grade resin used in applications such as rods, slabs, and tubing. Other applications include wire jacketing and centrifugal casting which require good dielectric properties, toughness, and fatigue resistance. Optimum processing conditions should provide a melt temperature of 480 - 500°F at the die.ALM, Nylene Canada, and Custom Resins are all operting companies of Polymeric Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nylene-600-Nylon-6-50-RH-Extrusion-Grade.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in³	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	62.0 MPa	8990 psi	ASTM D638
Elongation at Break	200 %	200 %	ASTM D638
Flexural Yield Strength	28.0 MPa	4060 psi	ASTM D790
Izod Impact, Notched	3.10 J/cm	5.81 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	175 °C	347 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	ASTM D648

Processing Properties	Metric	English	Comments
Processing Temperature	255 °C	491 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China