

Nylene® PA6 Glass Filled 5243 HS Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

Material Notes:

43% Glass Filled; Property data for dry as molded samples. ALM, Nylene Canada, and Custom Resins are all operating companies of Polymeric Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nylene-PA6-Glass-Filled-5243-HS-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.49 g/cc	0.0538 lb/in ³	ASTM D955
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	180 MPa	26100 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Izod Impact, Notched	1.10 J/cm	2.06 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	216 °C	421 °F	ASTM D3418
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China