

## Nylene® PA6/6 Glass Filled 5105 HS Nylon 6/6

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Glass Fiber Filled

**Material Notes:**

5% Glass Filler; Property data for dry as molded samples. ALM, Nylene Canada, and Custom Resins are all operating companies of Polymeric Resources Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nylene-PA66-Glass-Filled-5105-HS-Nylon-66.php](http://www.lookpolymers.com/polymer_Nylene-PA66-Glass-Filled-5105-HS-Nylon-66.php)

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in <sup>3</sup>	
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	ASTM D955

Thermal Properties	Metric	English	Comments
Melting Point	254 °C	489 °F	ASTM D3418

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China