

Nylene® PA6/6 Glass Filled 5150 HS Nylon 6/6

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 50% Glass Fiber Filled

Material Notes:

50% Glass Filler; Property data for dry as molded samples. ALM, Nylene Canada, and Custom Resins are all operating companies of Polymeric Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nylene-PA66-Glass-Filled-5150-HS-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.56 g/cc	0.0564 lb/in ³	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Thermal Properties	Metric	English	Comments
Melting Point	254 °C	489 °F	ASTM D3418

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China