

Nylene® PA6/6 Homopolymer 134 HSL Nylon 6/6

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Nucleated

Material Notes:

Low Viscosity Nucleated Grade; Property data for dry as molded samples. ALM, Nylene Canada, and Custom Resins are all operating companies of Polymeric Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nylene-PA66-Homopolymer-134-HSL-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	
Linear Mold Shrinkage	0.013 cm/cm	0.013 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	90.0 MPa	13100 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Flexural Modulus	3.25 GPa	471 ksi	ASTM D790
Izod Impact, Notched	0.400 J/cm	0.749 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	254 °C	489 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	235 °C	455 °F	
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China