

## Okulen® 500 - REG PE Multicoloured fine

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

### Material Notes:

OKULEN® 500 is a high molecular low pressure polyethylene with a molecular weight of approximately 500 g/mol. Applications include the food industry and sports center construction. It does an excellent job with its impact strength and insulating properties.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Okulen-500-REG-PE-Multicoloured-fine.php](http://www.lookpolymers.com/polymer_Okulen-500-REG-PE-Multicoloured-fine.php)

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in <sup>3</sup>	ISO 1183-A
Water Absorption	<= 0.10 %	<= 0.10 %	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	64 - 65 @Thickness 5.00 mm	64 - 65 @Thickness 0.197 in	3 s value; plate; ISO 868
Tensile Strength, Yield	10.0 - 20.0 MPa	1450 - 2900 psi	50 mm/min; ISO/R 527
Elongation at Break	>= 50 %	>= 50 %	50 mm/min; ISO/R 527
Creep Strength	10.0 MPa @Temperature 20.0 °C, Time 605000 sec	1450 psi @Temperature 68.0 °F, Time 168 hour	
Charpy Impact Unnotched	1.00 - 1.50 J/cm <sup>2</sup>	4.76 - 7.14 ft-lb/in <sup>2</sup>	ISO 11542-2
Coefficient of Friction, Dynamic	0.20 @Pressure 2.00 MPa	0.20 @Pressure 290 psi	PE-metal, V = 10 m/min; ASTM D1894
Abrasion	400 - 500	400 - 500	Slurry-Test rel to GUR 4120 = 100%; DIN 58836

Thermal Properties	Metric	English	Comments
CTE, linear	200 µm/m-°C	111 µin/in-°F	DIN 53752
Melting Point	130 - 135 °C	266 - 275 °F	DSC ISO 3146
Maximum Service Temperature, Air	80.0 °C	176 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	<= 1.00e+12 ohm-cm	<= 1.00e+12 ohm-cm	Teil 30; IEC 600093 / VDE 0303
Surface Resistance	<= 1.00e+11 ohm	<= 1.00e+11 ohm	Teil 30; IEC 60093 / VDE 0303

Electrical Properties

Metric

English

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China