

## Osprey Metals HTN 1A Brazing Powder

Category : Metal , Nonferrous Metal , Nickel Alloy , Solder/Braze Alloy

### Material Notes:

Particle size distribution 1-250 microns.SHAPE: Predominantly spherical PACKAGING: 4 & 20 Kg. Chemical composition and particle size distribution can be adjusted to suit customers' requirements.The specifications listed are subject to the benefits and scrutiny of Osprey's accreditation to ISO 9001. If the product delivered does not substantially meet the specification, Osprey will replace it. Osprey's liability is limited to the cost of replacement. Information provided to MatWeb by Osprey Metals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Osprey-Metals-HTN-1A-Brazing-Powder.php](http://www.lookpolymers.com/polymer_Osprey-Metals-HTN-1A-Brazing-Powder.php)

Thermal Properties	Metric	English	Comments
Melting Point	980 - 1070 °C	1800 - 1960 °F	
Solidus	980 °C	1800 °F	
Liquidus	1070 °C	1960 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 0.050 %	<= 0.050 %	
Boron, B	2.75 - 3.5 %	2.75 - 3.5 %	
Carbon, C	<= 0.060 %	<= 0.060 %	
Chromium, Cr	13 - 15 %	13 - 15 %	
Cobalt, Co	<= 0.10 %	<= 0.10 %	
Iron, Fe	4.0 - 5.0 %	4.0 - 5.0 %	
Nickel, Ni	73.875 %	73.875 %	
Phosphorous, P	<= 0.020 %	<= 0.020 %	
Silicon, Si	4.0 - 5.0 %	4.0 - 5.0 %	
Sulfur, S	<= 0.020 %	<= 0.020 %	
Titanium, Ti	<= 0.050 %	<= 0.050 %	
Zirconium, Zr	<= 0.050 %	<= 0.050 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**