

## Ovation Polymers Nemcon™ H PC DP113/X5 Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

Polycarbonate-Thermally conducting, electrically insulating grade with high HDT and improved processability. Information provided by Ovation Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ovation-Polymers-Nemcon-H-PC-DP113X5-Polycarbonate.php](http://www.lookpolymers.com/polymer_Ovation-Polymers-Nemcon-H-PC-DP113X5-Polycarbonate.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.56 g/cc	1.56 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	45.0 MPa	6530 psi	50 mm/min; ASTM D638
Elongation at Break	3.45 %	3.45 %	50 mm/min; ASTM D638
Tensile Modulus	2.45 GPa	355 ksi	50 mm/min; ASTM D638
Flexural Strength	75.0 MPa	10900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.95 GPa	428 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.587 J/cm @Temperature 23.0 °C	1.10 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.80 W/m-K	12.5 BTU-in/hr-ft <sup>2</sup> -°F	ASTM E-1461
Deflection Temperature at 1.8 MPa (264 psi)	124 °C @Thickness 3.20 mm	255 °F @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	1.00e+12 ohm	1.00e+12 ohm	ASTM D257

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China