

Ovation Polymers Opnyl OP6GF33 Nylon 6, 33% Glass Reinforced, Dry

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Nylon 6 - Glass reinforced (33 %), high tensile strength, stiffness and HDT. *All properties are measured after 48 hours of conditioning at 23°C and 50% relative humidity. For Nylon compounds the measurements are done in dry and wet conditions. All samples are prepared according to ASTM standards. Variations within normal tolerances are possible for various types of colors and functional properties like UV resistance. Information provided by Ovation Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ovation-Polymers-Opnyl-OP6GF33-Nylon-6-33-Glass-Reinforced-Dry.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D792
Linear Mold Shrinkage	0.0015 - 0.0025 cm/cm @Thickness 3.17 mm	0.0015 - 0.0025 in/in @Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	180 MPa	26100 psi	50 mm/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	50 mm/min; ASTM D638
Tensile Modulus	9.00 GPa	1310 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	230 MPa	33400 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	9.10 GPa	1320 ksi	1.3 mm/min; ASTM D790
Izod Impact, Notched	1.201 J/cm	2.250 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	216 °C @Thickness 3.20 mm	421 °F @Thickness 0.126 in	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	208 °C @Thickness 3.20 mm	406 °F @Thickness 0.126 in	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China