

## Ovation Polymers Opnyl OP6GF50 Nylon 6, 50% Glass Reinforced, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6

### Material Notes:

Nylon 6 - Glass reinforced (50 %), high tensile strength, stiffness and HDT. \*All properties are measured after 48 hours of conditioning at 23°C and 50% relative humidity. For Nylon compounds the measurements are done in dry and wet conditions. All samples are prepared according to ASTM standards. Variations within normal tolerances are possible for various types of colors and functional properties like UV resistance. Information provided by Ovation Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ovation-Polymers-Opnyl-OP6GF50-Nylon-6-50-Glass-Reinforced-Conditioned.php](http://www.lookpolymers.com/polymer_Ovation-Polymers-Opnyl-OP6GF50-Nylon-6-50-Glass-Reinforced-Conditioned.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.59 g/cc	1.59 g/cc	ASTM D792
Linear Mold Shrinkage	0.0020 - 0.0040 cm/cm @Thickness 3.17 mm	0.0020 - 0.0040 in/in @Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	150 MPa	21800 psi	50 mm/min; ASTM D638
Elongation at Break	4.0 %	4.0 %	50 mm/min; ASTM D638
Tensile Modulus	6.00 GPa	870 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	180 MPa	26100 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	8.80 GPa	1280 ksi	1.3 mm/min; ASTM D790

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China