

Ovation Polymers OpteSTAT™ NC PK 8010 Polyetheretherketone based Carbon Nanotube Compound

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Carbon Fiber Filled

Material Notes:

Material resistivity can be tailored to the application, while retaining the physical and thermal properties of the base polymer. Applications include components of disk drives, business machines or other electronic assemblies where ESD control is required while retaining exceptional cleanliness, dimensional control and physical propertiesAll properties after 48hrs conditioning at 23°C/50% RH

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ovation-Polymers-OpteSTAT-NC-PK-8010-Polyetheretherketone-based-Carbon-Nanotube-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.34 g/cc	1.34 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	95.0 MPa	13800 psi	50 mm/min; ASTM D638
Tensile Modulus	2.90 GPa	421 ksi	50 mm/min; ASTM D638
Flexural Modulus	2.80 GPa	406 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.801 J/cm @Temperature 23.0 °C	1.50 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	150 °C @Thickness 3.20 mm	302 °F @Thickness 0.126 in	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	10000 - 1.00e+7 ohm	10000 - 1.00e+7 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China