

Ovation Polymers UTTAP QU HT530 GF Nylon, 30% Glass Reinforced

Category : Polymer , Thermoplastic , Nylon

Material Notes:

Glass reinforced (30 %) - High Temperature Polyamide Alloy, excellent chemical and electrical resistance, high stiffness, modulus and HDT.

*All properties are measured after 48 hours of conditioning at 23°C and 50% relative humidity. All samples are prepared according to ASTM standards. Variations within normal tolerances are possible for various types of colors and functional properties like UV resistance. Information provided by Ovation Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ovation-Polymers-UTTAP-QU-HT530-GF-Nylon-30-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.48 g/cc	1.48 g/cc	ASTM D792
Water Absorption	0.80 %	0.80 %	24 hours; ASTM D570

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	160 MPa	23200 psi	50 mm/min; ASTM D638
Elongation at Break	3.5 %	3.5 %	50 mm/min; ASTM D638
Tensile Modulus	6.00 GPa	870 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	205 MPa	29700 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	10.5 GPa	1520 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.700 J/cm	1.31 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	220 °C @Thickness 3.20 mm	428 °F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	218 °C @Thickness 3.20 mm	424 °F @Thickness 0.126 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China