

## PCC-Advanced Forming Technology AlSiC-SD Metal Matrix Composite

Category : Metal , Metal Matrix Composite

**Material Notes:**

AlSiC metal matrix composites are formed by pressure infiltrating molten aluminum into silicon carbide preforms. This method of casting is typically used in applications where solution requirements include high strength, lightweight, custom CTE and high thermal conductivity.

PCC offers AlSiC with a composition varying between 30% to 74% silicon carbide by volume, depending on the application. This flexible material system allows PCC Composites to produce a part that can be tailored to exact solution requirements. Information provided by PCC-Advanced Forming Technology.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PCC-Advanced-Forming-Technology-AlSiC-SD-Metal-Matrix-Composite.php](http://www.lookpolymers.com/polymer_PCC-Advanced-Forming-Technology-AlSiC-SD-Metal-Matrix-Composite.php)

Physical Properties	Metric	English	Comments
Density	3.02 g/cc	0.109 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	88	88	
Tensile Strength, Ultimate	249 MPa	36100 psi	
Modulus of Elasticity	246 GPa	35700 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	7.30 $\mu\text{m}/\text{m}\cdot\text{C}$	4.06 $\mu\text{in}/\text{in}\cdot\text{F}$	X-Direction
	@Temperature 20.0 - 30.0 $^{\circ}\text{C}$	@Temperature 68.0 - 86.0 $^{\circ}\text{F}$	
	8.10 $\mu\text{m}/\text{m}\cdot\text{C}$	4.50 $\mu\text{in}/\text{in}\cdot\text{F}$	Y-Direction
	@Temperature 20.0 - 30.0 $^{\circ}\text{C}$	@Temperature 68.0 - 86.0 $^{\circ}\text{F}$	
Thermal Conductivity	175 W/m-K	1210 BTU-in/hr-ft <sup>2</sup> - $^{\circ}\text{F}$	
Melting Point	557 - 613 $^{\circ}\text{C}$	1030 - 1140 $^{\circ}\text{F}$	
Solidus	557 $^{\circ}\text{C}$	1030 $^{\circ}\text{F}$	
Liquidus	613 $^{\circ}\text{C}$	1140 $^{\circ}\text{F}$	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China