

PPT BP125 NiZn Ferrite Powder

Category : Ceramic , Oxide

Material Notes:

Uses: EMI Suppressors, Wave Absorbing Tiles, Impeders, Multi-Hole Connectors, Inductors, Transformers, Converters, Choke Coils, Antennas
Electromagnetic characteristics were tested on toroid with a HP4294A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PPT-BP125-NiZn-Ferrite-Powder.php

Physical Properties	Metric	English	Comments
Bulk Density	1.50 g/cc	0.0542 lb/in ³	typical
Particle Size	120 µm	120 µm	median granule size

Thermal Properties	Metric	English	Comments
Shrinkage	10.5 %	10.5 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1e+8 ohm-cm	1e+8 ohm-cm	
Magnetic Coercive Force, Hc	1.6 Oe	1.6 Oe	
Magnetic Remanence, Br	1200 Gauss	1200 Gauss	
Curie Temperature	350 °C	662 °F	

Processing Properties	Metric	English	Comments
Moisture Content	0.30 %	0.30 %	
Sintering Temperature	1270 °C @Time 10800 sec	2320 °F @Time 3.00 hour	

Descriptive Properties	Value	Comments
Flux Density Bs	3000 Gauss	Field Strength = 30 Oe
Initial Permeability, µi	125	
Q Factor (w/ 10 turns)	300	2 MHz

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China