

## PPT LSF120 Low Sintering Temperature Ferrite Powder

Category : Ceramic , Oxide

**Material Notes:**

Uses: Low Temperature Co-fired Ceramic Components (LTCC), Multi-Layer Chip Inductors (MLCI), Chip Beads (EMI Suppressors) Electromagnetic properties reported were tested on sintered toroids with a HP4294A.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PPT-LSF120-Low-Sintering-Temperature-Ferrite-Powder.php](http://www.lookpolymers.com/polymer_PPT-LSF120-Low-Sintering-Temperature-Ferrite-Powder.php)

Physical Properties	Metric	English	Comments
Bulk Density	3.20 g/cc	0.116 lb/in <sup>3</sup>	pressed
Density	5.20 g/cc	0.188 lb/in <sup>3</sup>	Sintered
Particle Size	0.5 μm	0.5 μm	mean
Specific Surface Area	5.5 m <sup>2</sup> /g	5.5 m <sup>2</sup> /g	

Thermal Properties	Metric	English	Comments
Shrinkage	15.5 %	15.5 %	

Electrical Properties	Metric	English	Comments
Curie Temperature	200 °C	392 °F	

Processing Properties	Metric	English	Comments
Moisture Content	0.30 %	0.30 %	
Sintering Temperature	900 °C	1650 °F	
	@Time 7200 sec	@Time 2.00 hour	

Descriptive Properties	Value	Comments
Initial Permeability, μi	140	
Q Factor (w/ 10 turns)	180	
Test Frequency	1 MHz	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China