

PTS Trimid® N6-G13L 13% GFR Lubricated Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 10% Glass Fiber Filled

Material Notes:

Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

http://www.lookpolymers.com/polymer_PTS-Trimid-N6-G13L-13-GFR-Lubricated-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	ASTM D792
Water Absorption	1.0 %	1.0 %	ASTM D570
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	110.3 MPa	16000 psi	ASTM D638
Elongation at Break	8.0 %	8.0 %	ASTM D638
Flexural Yield Strength	151.7 MPa	22000 psi	ASTM D790
Flexural Modulus	3.45 GPa	500 ksi	ASTM D790
Izod Impact, Notched	0.800 J/cm @Thickness 3.17 mm	1.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	<= 216 °C	<= 420 °F	
Middle Barrel Temperature	227 - 254 °C	440 - 490 °F	
Front Barrel Temperature	238 - 266 °C	460 - 510 °F	
Nozzle Temperature	238 - 266 °C	460 - 510 °F	
Melt Temperature	232 - 271 °C	450 - 520 °F	
Mold Temperature	21.1 - 93.3 °C	70.0 - 200 °F	
Drying Temperature	82.2 °C	180 °F	
Dry Time	3 - 4 hour	3 - 4 hour	
Injection Pressure	82.7 - 172 MPa	12000 - 25000 psi	
Back Pressure	0.000 - 0.345 MPa	0.000 - 50.0 psi	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China