

**PTS Trimid® N6-G33L 33% GFR Lubricated Nylon 6**

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

**Material Notes:**

Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PTS-Trimid-N6-G33L-33-GFR-Lubricated-Nylon-6.php](http://www.lookpolymers.com/polymer_PTS-Trimid-N6-G33L-33-GFR-Lubricated-Nylon-6.php)

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in <sup>3</sup>	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	137.9 MPa	20000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Modulus	6.90 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.800 J/cm @Thickness 3.17 mm	1.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	210 °C	410 °F	ASTM D789
Deflection Temperature at 1.8 MPa (264 psi)	204 °C	399 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	<= 216 °C	<= 420 °F	
Middle Barrel Temperature	227 - 254 °C	440 - 490 °F	
Front Barrel Temperature	238 - 266 °C	460 - 510 °F	
Nozzle Temperature	238 - 266 °C	460 - 510 °F	
Melt Temperature	232 - 271 °C	450 - 520 °F	
Mold Temperature	21.1 - 93.3 °C	70.0 - 200 °F	
Drying Temperature	82.2 °C	180 °F	
Dry Time	3 - 4 hour	3 - 4 hour	
Injection Pressure	82.7 - 172 MPa	12000 - 25000 psi	

Back Pressure Processing Properties	0.000 - 0.345 MPa Metric	0.000 - 50.0 psi English	Comments
Screw Speed	40 - 80 rpm	40 - 80 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China