

## PTS Trimid® N66-G13L 13% Glass Fiber Reinforced Lubed Nylon 6/6

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Glass Fiber Filled

### Material Notes:

Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PTS-Trimid-N66-G13L-13-Glass-Fiber-Reinforced-Lubed-Nylon-66.php](http://www.lookpolymers.com/polymer_PTS-Trimid-N66-G13L-13-Glass-Fiber-Reinforced-Lubed-Nylon-66.php)

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in <sup>3</sup>	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	117 MPa @Thickness 3.17 mm	17000 psi @Thickness 0.125 in	ASTM D638
Elongation at Break	3.0 % @Thickness 3.17 mm	3.0 % @Thickness 0.125 in	ASTM D638
Flexural Modulus	6.80 GPa @Thickness 3.17 mm	986 ksi @Thickness 0.125 in	ASTM D790
Izod Impact, Notched	0.900 J/cm @Thickness 3.17 mm	1.69 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	254 °C	489 °F	ASTM D789
Deflection Temperature at 1.8 MPa (264 psi)	243 °C	469 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	254 °C	490 °F	
Middle Barrel Temperature	268 °C	515 °F	
Front Barrel Temperature	285 °C	545 °F	
Nozzle Temperature	266 - 282 °C	510 - 540 °F	
Melt Temperature	271 - 293 °C	520 - 560 °F	
Mold Temperature	26.7 - 93.3 °C	80.0 - 200 °F	
Drying Temperature	71.1 °C	160 °F	

<small>Unit: MPa</small> Processing Properties	<small>4 hour</small> Metric	<small>4 hour</small> English	Comments
Injection Pressure	68.9 MPa	10000 psi	
Back Pressure	0.0689 - 0.689 MPa	10.0 - 100 psi	
Screw Speed	30 - 60 rpm	30 - 60 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China