

**PTS Trimid® N66-G33 33% Glass Fiber Reinforced Nylon 6/6**

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

**Material Notes:**

Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PTS-Trimid-N66-G33-33-Glass-Fiber-Reinforced-Nylon-66.php](http://www.lookpolymers.com/polymer_PTS-Trimid-N66-G33-33-Glass-Fiber-Reinforced-Nylon-66.php)

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in <sup>3</sup>	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	158.6 MPa	23000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	0.960 J/cm @Thickness 3.17 mm	1.80 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	254 °C	489 °F	ASTM D789
Deflection Temperature at 1.8 MPa (264 psi)	243 °C	469 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	254 °C	490 °F	
Middle Barrel Temperature	268 °C	515 °F	
Front Barrel Temperature	285 °C	545 °F	
Nozzle Temperature	266 - 282 °C	510 - 540 °F	
Melt Temperature	271 - 293 °C	520 - 560 °F	
Mold Temperature	26.7 - 93.3 °C	80.0 - 200 °F	
Drying Temperature	71.1 °C	160 °F	
Dry Time	4 hour	4 hour	
Injection Pressure	68.9 MPa	10000 psi	

Back Pressure Processing Properties	0.0689 - 0.689 MPa Metric	10.0 - 100 psi English	Comments
Screw Speed	30 - 60 rpm	30 - 60 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China