

## Palm Labs Adhesives TURBO FUSE SERIES 110 MEDICAL DEVICES APPROVED (100 Viscosity) Rapid Bonding Adhesive

Category : Polymer , Adhesive

### Material Notes:

Palm Lab's Cyanoacrylate is a one component rapid bonding adhesive. TURBO FUSE SERIES 130 - MEDICAL DEVICES APPROVED advanced formula is designed to polymerize instantly by absorbing surface moisture. The product's performance has been tested with a variety of materials, and is recommended for a multitude of applications. The fast curing qualities make it especially desirable in high speed industrial production. TURBO FUSE SERIES 130 - MEDICAL DEVICES APPROVED is ideal for use in applications that require an easily handled medium viscosity adhesive approved for use on Medical Devices. Part Numbers for this data: 04-130M, 10-130M, 15-130M, 20-130M, 25-130M, 30-130M Soluble in Acetone, MEK, Amide, Methylene Chloride Information provided by Palm Laboratories Adhesives

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Palm-Labs-Adhesives-TURBO-FUSE-SERIES-110-MEDICAL-DEVICES-APPROVED-100-Viscosity-Rapid-Bonding-Adhesive.php](http://www.lookpolymers.com/polymer_Palm-Labs-Adhesives-TURBO-FUSE-SERIES-110-MEDICAL-DEVICES-APPROVED-100-Viscosity-Rapid-Bonding-Adhesive.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	Liquid State
Viscosity	90 - 110 cP	90 - 110 cP	Liquid State

Mechanical Properties	Metric	English	Comments
Hardness, Barcol	65	65	Cured State
Shear Strength	17.2 MPa	2500 psi	Tensile, (Cured State)

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	82.2 °C	180 °F	Cured State
Softening Point	149 °C	300 °F	Cured State
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	Cured State
Flash Point	76.7 - 93.3 °C	170 - 200 °F	Liquid State

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.33 @Frequency 1.00e+6 Hz	3.33 @Frequency 1.00e+6 Hz	Cured State

Processing Properties	Metric	English	Comments
Shelf Life	12.0 Month	12.0 Month	Liquid State

Descriptive Properties	Value	Comments
Appearance	Clear Liquid	Liquid State
	Clear-Hard	Cured State
Base compound (Resin)	Ethyl Cyanoacrylate	Liquid State
Gap Fill	0.005"	Cured State
Material Set Up Time	<5 sec	Rubber to Rubber
	10-30 sec	Steel to Steel
	5-10 sec	Phenolic to Phenolic
	5-10 sec	Aluminum to Aluminum
	5-15 sec	Polycarbonate to Polycarbonate

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China