

Park Electrochemical Nelco® N4000-13 BC® Buried Capacitance™, High-Speed Multifunctional Epoxy Laminate and Prepreg

Category : Polymer , Thermoset , Epoxy

Material Notes:

The Nelco N4000-13 series is an enhanced epoxy resin system engineered to provide both outstanding thermal and high signal speed / low signal loss properties. The Nelco N4000-13 BC® is offered as a buried capacitance solution, offering a greater degree of design freedom for smaller, more reliable assemblies. Key Features and Benefits: Tg >210°C, outstanding thermal, electrical and signal loss properties CAF Resistant Buried Capacitance Solution Proprietary advanced resin technology High-Tg FR-4 processing Available in a variety of constructions Applications/Qualifications: High Density Interconnects Fine-Line Multilayers Backplanes Surface-Mount Multilayers BGA Multilayers MCM-Ls CSP Attachment Wireless Communications Infrastructure High Speed Services High Speed Storage Networks Internet Switching / Routing Systems Information provided by Park Electrochemical Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Park-Electrochemical-Nelco-N4000-13-BC-Buried-Capacitance-High-Speed-Multifunctional-Epoxy-Laminate-and-Prepreg.php

Physical Properties	Metric	English	Comments
Density	1.77 g/cc	0.0639 lb/in ³	50% Resin Content; Internal Method
Water Absorption	0.10 %	0.10 %	IPC-TM-650.2.6.2.1

Mechanical Properties	Metric	English	Comments
Peel Strength	1.31 kN/m	7.50 pli	after solder float; IPC-TM-650.2.4.8
	1.42 kN/m	8.10 pli	at elevated temperature; IPC-TM-650.2.4.8.2a
	1.58 kN/m	9.00 pli	after exposure to process solutions; IPC-TM-650.2.4.8

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.21 J/g-°C	0.290 BTU/lb-°F	ASTM E1461
Thermal Conductivity	0.350 W/m-K	2.43 BTU-in/hr-ft ² -°F	ASTM E1461
Glass Transition Temp, Tg	200 °C	392 °F	TMA; IPC-TM-650.2.4.24c
	210 °C	410 °F	DSC; IPC-TM-650.2.4.25c
	240 °C	464 °F	DMA (Tan δ Peak); IPC-TM-650.2.4.24.3
Decomposition Temperature	365 °C	689 °F	5% weight loss; TGA; IPC-TM-650.2.4.24.6
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.2	3.2	Stripline; IPC-TM-650.2.5.5.5
	@Frequency 1.00e+10 Hz	@Frequency 1.00e+10 Hz	
	3.3	3.3	
Dielectric Strength	@Frequency 1.00e+9 Hz	@Frequency 1.00e+9 Hz	RF Impedance; IPC-TM-650.2.5.5.9
	3.3	3.3	Split Post Cavity
	@Frequency 2.50e+9 Hz	@Frequency 2.50e+9 Hz	
Dielectric Strength	47.2 kV/mm	1200 kV/in	IPC-TM-650.2.5.6.2
Dissipation Factor	0.0080	0.0080	Split Post Cavity
	@Frequency 2.50e+9 Hz	@Frequency 2.50e+9 Hz	
	0.0090	0.0090	
Dissipation Factor	@Frequency 1.00e+10 Hz	@Frequency 1.00e+10 Hz	Stripline; IPC-TM-650.2.5.5.5
	0.0080	0.0080	
	@Frequency 2.50e+9 Hz	@Frequency 2.50e+9 Hz	

Descriptive Properties	Value	Comments
Methylene Chloride Resistance (% Weight Change)	0.7	IPC-TM-650.2.3.4.3
T260 (minutes)	>30	IPC-TM-650.2.4.24.1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China