

## Park Electrochemical Nelcote® E-765 Epoxy Prepreg, T700 12K 2x2 Twill Reinforced

Category : Polymer , Thermoset , Epoxy

### Material Notes:

Nelcote® E-765 is a tough 250°F cure prepreg system designed to replace 350°F cure systems in aircraft structural applications. FAA-approved Design Allowable Databases are available upon request. Key Features and Benefits: Designed to replace first generation 350°F (176°C) cure systems. Wide cure temperature process window of 250°F to 350°F Exhibits very low void content, i.e.,

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Park-Electrochemical-Nelcote-E-765-Epoxy-Prepreg-T700-12K-2x2-Twill-Reinforced.php](http://www.lookpolymers.com/polymer_Park-Electrochemical-Nelcote-E-765-Epoxy-Prepreg-T700-12K-2x2-Twill-Reinforced.php)

Physical Properties	Metric	English	Comments
Volatiles	<= 1.5 %	<= 1.5 %	
Thickness	381 microns	15.0 mil	cured, per ply

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	841 MPa @Temperature 21.1 °C	122000 psi @Temperature 70.0 °F	0° Direction, Dry; Vacuum/Oven Cured; ASTM D3039-95
Tensile Modulus	57.9 GPa @Temperature 21.1 °C	8400 ksi @Temperature 70.0 °F	0° Direction, Dry; Vacuum/Oven Cured; ASTM D3039-95
Compressive Strength	738 MPa @Temperature 21.1 °C	107000 psi @Temperature 70.0 °F	Dry; Vacuum/Oven Cured; SACMA 1-94
Compressive Modulus	55.8 GPa @Temperature 21.1 °C	8100 ksi @Temperature 70.0 °F	Dry; Vacuum/Oven Cured; SACMA 1-94
Shear Strength	60.7 MPa @Temperature 21.1 °C	8800 psi @Temperature 70.0 °F	Short-Beam, Dry; Vacuum/Oven Cured; ASTM D2344

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	165 °C	329 °F	Dry; DMA

Processing Properties	Metric	English	Comments
Gel Time	2.00 - 6.00 min @Temperature 135 °C	2.00 - 6.00 min @Temperature 275 °F	
Shelf Life	6.00 Month @Temperature -17.8 °C	6.00 Month @Temperature 0.000 °F	

Descriptive Properties	Value	Comments
Fabric Area Weight (g/m <sup>2</sup> )	370	
Prepreg Resin Content (%)	37-43	
Resin Flow (%)	12-24	275°F, 15psi
Tack	Light-Medium	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China