

Parker Chomerics CHO-SEAL 1217 Conductive Elastomer

Category : Polymer , Thermoset , Fluoropolymer, TS , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Resists highest level of EMP induced current; military gasket of choice in non-corrosive environments; excellent processing for molding and extrusion. Molded and ExtrudedRoHS Compliant Information provided by Chomerics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Parker-Chomerics-CHO-SEAL-1217-Conductive-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	3.50 - 4.50 g/cc	3.50 - 4.50 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70 - 80	70 - 80	ASTM D2240
Tensile Strength at Break	>= 1.24 MPa	>= 180 psi	ASTM D412
Elongation at Break	100 - 300 %	100 - 300 %	ASTM D412
Tear Strength	6.13 kN/m	35.0 pli	ASTM D624
Compression Set	<= 35 % @Temperature 100 °C, Time 252000 sec	<= 35 % @Temperature 212 °F, Time 70.0 hour	ASTM D395 Method B

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	
Minimum Service Temperature, Air	-55.0 °C	-67.0 °F	Flex TR10; ASTM D1329

Electrical Properties	Metric	English	Comments
Volume Resistivity	0.010 ohm-cm	0.010 ohm-cm	as supplied without pressure sensitive adhesive; MIL-DTL-83528
	<= 0.15 ohm-cm	<= 0.15 ohm-cm	Post Tensile Set; MIL-DTL-83528 Para.4.6.9
Shielding Effectiveness	>= 70 dB @Frequency 200000 Hz	>= 70 dB @Frequency 200000 Hz	H Field; MIL-DTL-83528 Para.4.6.12
	>= 110 dB @Frequency 1.00e+10 Hz	>= 110 dB @Frequency 1.00e+10 Hz	E Field; MIL-DTL-83528 Para.4.6.12
	>= 115 dB	>= 115 dB	E Field; MIL-DTL-83528 Para.4.6.12

Electrical Properties	@Frequency 2.00e+9 Metric Hz	@Frequency 2.00e+9 English Hz	Comments
	>= 120 dB	>= 120 dB	Plane Wave; MIL-DTL-83528 Para.4.6.12
	@Frequency 1.00e+8 Hz	@Frequency 1.00e+8 Hz	
	>= 120 dB	>= 120 dB	Plane Wave; MIL-DTL-83528 Para.4.6.12
	@Frequency 5.00e+8 Hz	@Frequency 5.00e+8 Hz	

Descriptive Properties	Value	Comments
Binder	Fluoro-silicone	
EMP Survivability	>0.9 kA / in	MIL-DTL-83528 Para.4.6.16
Filler	Ag/Cu	
Heat Aging	<0.015 ohm-cm	MIL-DTL-83528 Para.4.6.15
Type	C	MIL-DTL-83528
Vibration Resistance, After	<0.01 ohm-cm	MIL-DTL-83528 Para.4.6.13
Vibration Resistance, During	<0.015 ohm-cm	MIL-DTL-83528 Para.4.6.13

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China