

Parker Chomerics CHO-SHIELD® 1091 Adhesion Promoter for Conductive Polyurethane Coatings

Category : Polymer , Adhesive , Thermoset

Material Notes:

Information provided by Chomerics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Parker-Chomerics-CHO-SHIELD-1091-Adhesion-Promoter-for-Conductive-Polyurethane-Coatings.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.780 g/cc	0.780 g/cc	
Thickness	25.4 microns	1.00 mil	Recommended

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	82.0 °C	180 °F	
Minimum Service Temperature, Air	-55.0 °C	-67.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min @Temperature 23.0 °C	1.00 hour @Temperature 73.4 °F	
Shelf Life	15.0 Month	15.0 Month	

Descriptive Properties	Value	Comments
Consistency	Thin Fluid	
Mix Ratio	1-part	
Theoretical Coverage	1200 ft ² /lb	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China