

Parker Chomerics CHO-SHIELD® 1091 PRIMER

Category : Other Engineering Material , Additive/Filler for Polymer

Material Notes:

CHO-SHIELD 1091 is an air-drying liquid coating for enhancing the adhesion of CHO-SHIELD 2001 and 2003 corrosion resistant, electrically conductive coatings to chemically treated aluminum. CHO-SHIELD 1091 primer is a one-component system which cures at ambient temperatures. Information provided by Chomerics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Parker-Chomerics-CHO-SHIELD-1091-PRIMER.php

Physical Properties	Metric	English	Comments
Specific Gravity	6.50 g/cc	6.50 g/cc	
Viscosity	5.0 cP	5.0 cP	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	82.0 °C	180 °F	
Minimum Service Temperature, Air	-55.0 °C	-67.0 °F	
Flash Point	60.0 °C	140 °F	

Processing Properties	Metric	English	Comments
Cure Time	30.0 min	0.500 hour	
	@Temperature 88.0 °C	@Temperature 190 °F	
	60.0 min	1.00 hour	
	@Temperature 24.0 °C	@Temperature 75.2 °F	
Shelf Life	15.0 Month	15.0 Month	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China