

## Parker Chomerics CHO-SHIELD® 4937 Part B Barrier Coating Component

Category : Polymer , Adhesive

**Material Notes:**

Information provided by Chomerics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Parker-Chomerics-CHO-SHIELD-4937-Part-B-Barrier-Coating-Component.php](http://www.lookpolymers.com/polymer_Parker-Chomerics-CHO-SHIELD-4937-Part-B-Barrier-Coating-Component.php)

Physical Properties	Metric	English	Comments
Specific Gravity	>= 1.00 g/cc	>= 1.00 g/cc	
Volatiles	<= 5.0 %	<= 5.0 %	
Carbon Black Loading	1.0 %	1.0 %	

Thermal Properties	Metric	English	Comments
Flash Point	>= 134 °C	>= 273 °F	

Descriptive Properties	Value	Comments
1,4-Butanediol wt. % Max	5	
Dibutyltin dilaurate wt. % Min	5	
Diphenylmethane diisocyanate wt. % Max	20	
Ethyl Benzene wt. %	5	
Hexamethylene diisocyanate wt. % Max	2	
Mica wt. % Max	30	
n-Butyl Acetate wt. % Max	10	
Physical Form	Black liquid	
Polyisocyanate Polymer wt. % Min	60	
Polyol wt. % Min	60	
Silica, Crystalline Quartz wt. % Max	0.2	
Xylene wt. %	10	
Zinc Stearate wt. % Max	2	

**Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**