

Parker Chomerics THERM-A-GAP™ GEL 8010 High Performance Fully Cured Dispensable Gel

Category : Fluid

Material Notes:

Description: Parker Chomerics fully cured dispensable GELs eliminate time consuming hand assembly, decreasing installation costs and reducing customer manufacturing and purchasing (logistical) complexity. These products require no mixing or curing, providing superior design flexibility. Provides low thermal impedance at thin and thick gaps, allowing use of common heat spreaders; Lower temperature increases product life, typically a doubling of life based on every 10°C decrease in temperature; Deflects easily under very low compressive forces, decreasing stress on components thus decreasing component failures. Typical Applications: Automotive Electronic Control Units (ECU's), Power Supplies & Semiconductors, Memory & Power Modules, Microprocessors/Graphics Processors, and Flat Panel Displays & Consumer Electronics. Features/Benefits: Easily dispensable, Fully-cured/No pump out, High bulk thermal conductivity, Low thermal impedance, Ultra low compression force, High tack surface & reworkable and Proven long-term reliability. Product Attributes: Thin bondline gel (approximately 2-10 mils), Low thermal impedance gel, Stencil printable with no pump out, Ideal for high-volume dispensing, and Proven long-term reliability. Information provided by Chomerics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Parker-Chomerics-THERM-A-GAP-GEL-8010-High-Performance-Fully-Cured-Dispensable-Gel.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.70 g/cc	2.70 g/cc	ASTM D792
Thickness	>= 50.0 microns	>= 1.97 mil	Bondline thickness
Deformation	27 % @Pressure 0.00345 MPa	27 % @Pressure 0.500 psi	Dispensed 1.0 cc of material, Brought 1" x 1" probe down to 0.1"; Test rate 0.025 in/min; Modified ASTM C165
	45 % @Pressure 0.00689 MPa	45 % @Pressure 1.00 psi	Dispensed 1.0 cc of material, Brought 1" x 1" probe down to 0.1"; Test rate 0.025 in/min; Modified ASTM C165
	52 % @Pressure 0.0103 MPa	52 % @Pressure 1.50 psi	Dispensed 1.0 cc of material, Brought 1" x 1" probe down to 0.1"; Test rate 0.025 in/min; Modified ASTM C165
	57 % @Pressure 0.0138 MPa	57 % @Pressure 2.00 psi	Dispensed 1.0 cc of material, Brought 1" x 1" probe down to 0.1"; Test rate 0.025 in/min; Modified ASTM C165
	60 % @Pressure 0.0172 MPa	60 % @Pressure 2.50 psi	Dispensed 1.0 cc of material, Brought 1" x 1" probe down to 0.1"; Test rate 0.025 in/min; Modified ASTM C165
	63 % @Pressure 0.0207 MPa	63 % @Pressure 3.00 psi	Dispensed 1.0 cc of material, Brought 1" x 1" probe down to 0.1"; Test rate 0.025 in/min; Modified ASTM C165
	65 %	65 %	Dispensed 1.0 cc of material, Brought 1" x 1" probe down to 0.1"; Test rate

Physical Properties	@Pressure 0.0241 MPa Metric	@Pressure 3.50 psi English	0.025 in/min; Modified ASTM C165 Comments
Outgassing - Total Mass Loss	0.34 %	0.34 %	CVCM; ASTM E595
	1.33 %	1.33 %	TML; ASTM E595

Thermal Properties	Metric	English	Comments
CTE, linear	150 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	83.3 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM E831
Specific Heat Capacity	1.00 J/g $\cdot^{\circ}\text{C}$	0.239 BTU/lb $\cdot^{\circ}\text{F}$	ASTM E1269
Thermal Conductivity	3.00 W/m-K	20.8 BTU-in/hr-ft $^2\cdot^{\circ}\text{F}$	ASTM D5470
Maximum Service Temperature, Air	200 $^{\circ}\text{C}$	392 $^{\circ}\text{F}$	
Minimum Service Temperature, Air	-55.0 $^{\circ}\text{C}$	-67.0 $^{\circ}\text{F}$	
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Constant	6.3	6.3	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	8.00 kV/mm	203 kV/in	ASTM D149
Dissipation Factor	0.0020	0.0020	Chomerics
	@Frequency 100000 Hz	@Frequency 100000 Hz	

Processing Properties	Metric	English	Comments
Shelf Life	18.0 Month	18.0 Month	From date of Manufacture

Descriptive Properties	Value	Comments
Color	White	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China