

## Parker Chomerics Tecknit Consil®-II 842 Molded Silver-Filled Silicone Elastomer

Category : Polymer , Thermoset , Silicone

### Material Notes:

Description: CONSIL-II is a molded silicone elastomer filled with silver-coated inert particles. It provides high electrical conductivity, broadband shielding and moisture sealing. CONSIL-II is designed to provide reliable cost effective shielding for a wide range of EMI applications. CONSIL-II is manufactured in sheets, molded parts, strips, and die cut flat gaskets. Applications: CONSIL-II should be used where there is a need for high broadband shielding combined with excellent moisture sealing properties. Information provided by Chomerics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Parker-Chomerics-Tecknit-Consil-II-842-Molded-Silver-Filled-Silicone-Elastomer.php](http://www.lookpolymers.com/polymer_Parker-Chomerics-Tecknit-Consil-II-842-Molded-Silver-Filled-Silicone-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.61 - 2.11 g/cc	1.61 - 2.11 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60 - 80	60 - 80	ASTM D2240
Tensile Strength	>= 0.827 MPa	>= 120 psi	ASTM D412
Elongation at Break	>= 120 %	>= 120 %	ASTM D412
Tear Strength	7.89 kN/m	45.0 pli	ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	351 °F	
Minimum Service Temperature, Air	-51.0 °C	-59.8 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	<= 0.010 ohm-cm	<= 0.010 ohm-cm	
Shielding Effectiveness	75 dB	75 dB	H-Field
	@Frequency 100000 Hz	@Frequency 100000 Hz	
	90 dB	90 dB	Plane Wave
	@Frequency 1.00e+10 Hz	@Frequency 1.00e+10 Hz	
	>= 100 dB	>= 100 dB	Plane Wave
	@Frequency 1.00e+9 Hz	@Frequency 1.00e+9 Hz	
	130 dB	130 dB	

Electrical Properties	Metric	English	Comments
	@Frequency 1.00e+7 Hz	@Frequency 1.00e+7 Hz	

Descriptive Properties	Value	Comments
Binder	Silicone	
Color	Tan	
Filler	Silver-plated glass particles	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China