

Pasargad Polymer Peyvand Pasamid 3P-H1130W Nylon 6, 30% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

Material Notes:

Form: Pellets Processing Method: Injection Molding Uses: Automotive Application Furniture Appliance Components Electrical

Parts Fastener Housing Information provided by Pasargad Polymer Peyvand Co

Order this product through the following link:

http://www.lookpolymers.com/polymer_Pasargad-Polymer-Peyvand-Pasamid-3P-H1130W-Nylon-6-30-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	160 MPa	23200 psi	ISO 527-2
Elongation at Break	4.0 %	4.0 %	ISO 527-2
Tensile Modulus	9.00 GPa	1310 ksi	ISO 527-2
Charpy Impact Unnotched	8.50 J/cm ²	40.4 ft-lb/in ²	ISO 179/1eU
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ISO 11357-3
Deflection Temperature at 1.8 MPa (264 psi)	215 °C	419 °F	Unannealed; ISO 75-2/C

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	235 - 275 °C	455 - 527 °F	
Drying Temperature	90.0 °C	194 °F	
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Color	White	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China