

Perstorp Compounds Akestra™ 100 Thermoplastic Copolyester

Category : Polymer , Thermoplastic , Polyester, TP

Material Notes:

Excellent appearance, clarity, hydrolytic stability, heat resistance and high strength. Used for extrusion and injection molded articles, blow molding, films and sheets. It can be used as a polystyrene alternative for heat resistant thin wall containers, a polycarbonate alternative for durable "dishwasher proof" transparent products, and a glass alternative for hot-fill food containers. Information provided by Perstorp Compounds Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Perstorp-Compounds-Akestra-100-Thermoplastic-Copolyester.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength	55.0 MPa	7980 psi	
Elongation at Break	200 %	200 %	ASTM D638
Flexural Yield Strength	90.0 MPa	13100 psi	ASTM D790
Flexural Modulus	2.50 GPa	363 ksi	ASTM D790
Izod Impact, Notched	0.250 J/cm	0.468 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	100 °C	212 °F	ASTM D7426

Optical Properties	Metric	English	Comments
Haze	1.0 %	1.0 %	ASTM D1003
Transmission, Visible	91 %	91 %	ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China