

Petroquimica Triunfo Trithene® CX 7020 LDPE - Cast Film

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE

Material Notes:

The Trithene® CX 7020 resin is a low-density polyethylene (LDPE) with medium molecular weight, excellent processability, and low gel content. Those features allow a production of thin and highly uniform films. This product complies with ASTM standard D1248-IA3. Applications: Smooth or embossed films for diapers, disposable sheets, etc.; Films for lamination; Injection-Blow Molding. Resin Properties: Compressed molded plate. Method ASTM D-1928, procedure C. Film obtained on a 50mm blow film line with barrier screw, 25:1 L/D, 1.0mm die gap, 50µm gauge, 2.3:1 BUR. Information provided by Dax Resinas

Order this product through the following link:

http://www.lookpolymers.com/polymer_Petroquimica-Triunfo-Trithene-CX-7020-LDPE-Cast-Film.php

Physical Properties	Metric	English	Comments
Density	0.922 - 0.924 g/cc	0.0333 - 0.0334 lb/in ³	ASTM D1505
Thickness	50.0 microns	1.97 mil	
Melt Index of Compound	1.7 - 2.3 g/10 min @Load 2.16 kg, Temperature 190 °C	1.7 - 2.3 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	93	93	ASTM D2240
Tensile Strength at Break	12.5 MPa	1810 psi	ASTM D638
Tensile Strength, Yield	11.0 MPa	1600 psi	ASTM D638
Film Elongation at Break, MD	365 %	365 %	ASTM D882
Film Elongation at Break, TD	650 %	650 %	ASTM D882
Elongation at Break	550 %	550 %	ASTM D638
Secant Modulus, MD	0.0950 GPa	13.8 ksi	5%; ASTM D882
Secant Modulus, TD	0.100 GPa	14.5 ksi	5%; ASTM D882
Coefficient of Friction, Dynamic	0.65	0.65	ASTM D1894
Elmendorf Tear Strength, MD	8.40 g/micron	213 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	5.60 g/micron	142 g/mil	ASTM D1922
Dart Drop Test	140 g	0.309 lb	(method A); ASTM D1709
Film Tensile Strength at Break, MD	21.0 MPa	3050 psi	ASTM D882

Film Tensile Strength at Break, TD Mechanical Properties	19.0 MPa Metric	2760 psi English	ASTM D882 Comments
---	--------------------	---------------------	-----------------------

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Vicat Softening Point	94.0 °C	201 °F	ASTM D1525
-----------------------	---------	--------	------------

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Haze	7.0 %	7.0 %	ASTM D1003
------	-------	-------	------------

Gloss	109 %	109 %	@ 60° Gardner; ASTM D2457
-------	-------	-------	---------------------------

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Temperature	155 - 170 °C	311 - 338 °F	Plasticizing Zone
------------------------	--------------	--------------	-------------------

	165 - 175 °C	329 - 347 °F	Mixture Zone
--	--------------	--------------	--------------

Feed Temperature	145 - 160 °C	293 - 320 °F	
------------------	--------------	--------------	--

Adapter Temperature	175 - 190 °C	347 - 374 °F	
---------------------	--------------	--------------	--

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China