

Phillips 66 COPYLENE® CH008 Polypropylene, Homopolymer, Netting

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

COPYLENE™ CH008 is a fractional melt flow polypropylene homopolymer resin available in pellet form. Applications:

Raffia/Tapes/Strapping; Anti-Corrosion Coating; Geotextile & Agriculture; Nets. Replacement alternative for Pro-fax® HL781E Information provided by Phillips 66.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Phillips-66-COPYLENE-CH008-Polypropylene-Homopolymer-Netting.php

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in ³	ASTM D792
Melt Flow	0.80 g/10 min	0.80 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	34.8 MPa	5050 psi	2 in/min; ASTM D638
Elongation at Yield	11 %	11 %	ASTM D638
Flexural Modulus	1.52 GPa	220 ksi	0.05 in/min; 1% secant; Procedure A; ASTM D790
Izod Impact, Notched	0.641 J/cm	1.20 ft-lb/in	Method A; ASTM D256
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	unannealed; ASTM D648

Descriptive Properties	Value	Comments
Process	Extrusion	
Region	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China