

Phillips 66 COPYLENE® CH034EV Polypropylene, Homopolymer, Fiber, Tape, UV

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Fiber Grade

Material Notes:

COPYLENE™ CH034EV is a polypropylene homopolymer resin designed for fiber applications. Applications: Filament Yarn, Geotextile & agriculture. Equivalent to Pro-fax® HL348J Information provided by Phillips 66.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Phillips-66-COPYLENE-CH034EV-Polypropylene-Homopolymer-Fiber-Tape-UV.php

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in ³	ASTM D792
Melt Flow	3.4 g/10 min @Load 2.16 kg, Temperature 230 °C	3.4 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	36.5 MPa	5300 psi	2 in/min; ASTM D638
Elongation at Yield	11 %	11 %	ASTM D638
Flexural Modulus	1.45 GPa	210 ksi	0.05 in/min; 1% secant; Procedure A; ASTM D790
Izod Impact, Notched	0.427 J/cm @Temperature 23.0 °C	0.800 ft-lb/in @Temperature 73.4 °F	Method A; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	99.0 °C	210 °F	unannealed; ASTM D648

Descriptive Properties	Value	Comments
Process	Fiber	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

