

## Phillips 66 COPYLENE® CH200L Polypropylene, Homopolymer, CR, Antistat, Injection Molding

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

COPYLENE™ CH200L is designed for general purpose injection molding applications with anti-static and controlled rheology. Applications: Food Containers, Housewares, Closures. Information provided by Phillips 66.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Phillips-66-COPYLENE-CH200L-Polypropylene-Homopolymer-CR-Antistat-Injection-Molding.php](http://www.lookpolymers.com/polymer_Phillips-66-COPYLENE-CH200L-Polypropylene-Homopolymer-CR-Antistat-Injection-Molding.php)

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in <sup>3</sup>	ASTM D792
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 230 °C	20 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	33.1 MPa	4800 psi	2 in/min; ASTM D638
Elongation at Yield	10 %	10 %	ASTM D638
Flexural Modulus	1.34 GPa	195 ksi	0.05 in/min; 1% secant; Procedure A; ASTM D790
Izod Impact, Notched	0.374 J/cm @Temperature 23.0 °C	0.700 ft-lb/in @Temperature 73.4 °F	Method A; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	90.0 °C	194 °F	unannealed; ASTM D648

Descriptive Properties	Value	Comments
Process	Injection Molding	
Region	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China