

Phillips 66 COPYLENE® CH350LN Polypropylene, Homopolymer, High Flow, Nucleated, Lube, Injection Molding

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

COPYLENE™ CH350LN is designed for general purpose injection molding applications with anti-static, nucleation and controlled rheology.

Applications: Food Containers, Housewares, Closures. Information provided by Phillips 66.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Phillips-66-COPYLENE-CH350LN-Polypropylene-Homopolymer-High-Flow-Nucleated-Lube-Injection-Molding.php

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in ³	ASTM D792
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 230 °C	35 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	37.6 MPa	5450 psi	2 in/min; ASTM D638
Elongation at Yield	7.0 %	7.0 %	ASTM D638
Flexural Modulus	1.76 GPa	255 ksi	0.05 in/min; 1% secant; Procedure A; ASTM D790
Izod Impact, Notched	0.427 J/cm @Temperature 23.0 °C	0.800 ft-lb/in @Temperature 73.4 °F	Method A; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	119 °C	246 °F	unannealed; ASTM D648

Descriptive Properties	Value	Comments
Process	Injection Molding	
Region	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China