

## Phillips 66 COPYLENE® CH350V Polypropylene, Homopolymer, Extrusion Coating, Spunbound, Gas Fade & UV Resistant

Category: Polymer, Thermoplastic, Polypropylene (PP)

## **Material Notes:**

COPYLENE™ CH350V is a very high melt flow polypropylene homopolymer resin designed for fiber spinning. Applications: Food Packaging

Film, Heavy Duty Packaging, Absorption & Filtration, Filament Yarn, Furniture & Buildings, IBCs, Geotextile & Agriculture, Hygiene

Nonwoven, Protective Clothes, Wipes/Tissues. Equivalent to Pro-fax® HL344SInformation provided by Phillips 66.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Phillips-66-COPYLENE-CH350V-Polypropylene-Homopolymer-Extrusion-Coating-Spunbound-Gas-Fade-UV-Resistant.php

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in <sup>3</sup>	ASTM D792
Melt Flow	35 g/10 min	35 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Descriptive Properties	Value	Comments
Process	Fiber	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China