

## Phillips 66 COPYLENE® CM350LN Polypropylene, Impact Copolymer, Medium Impact, Nucleated, Antistat, Injection Molding

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

### Material Notes:

COPYLENE™ CM350LN is a high melt flow, controlled rheology, medium impact polypropylene copolymer resin designed for injection molding applications requiring a good balance of stiffness, impact, resistance and processability. Applications: Caps & closures, Opaque containers. Equivalent to Pro-fax® EL245S Information provided by Phillips 66.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Phillips-66-COPYLENE-CM350LN-Polypropylene-Impact-Copolymer-Medium-Impact-Nucleated-Antistat-Injection-Molding.php](http://www.lookpolymers.com/polymer_Phillips-66-COPYLENE-CM350LN-Polypropylene-Impact-Copolymer-Medium-Impact-Nucleated-Antistat-Injection-Molding.php)

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in <sup>3</sup>	ASTM D792
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 230 °C	35 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	22.8 MPa	3300 psi	2 in/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	ASTM D638
Flexural Modulus	1.21 GPa	175 ksi	0.05 in/min; 1% secant; Procedure A; ASTM D790
Izod Impact, Notched	1.07 J/cm @Temperature 23.0 °C	2.00 ft-lb/in @Temperature 73.4 °F	Method A; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	107 °C	225 °F	unannealed; ASTM D648

Descriptive Properties	Value	Comments
Process	Injection Molding	
Region	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China