

Phillips 66 COPYLENE® CR350CL-02 Polypropylene, Random Copolymer, Clarified

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

CR350CL-02 is a clarified, random copolymer specially designed for clear injection molding applications and is formulated with lube for excellent mold release. Potential Applications: Injection molding. Information provided by Phillips 66.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Phillips-66-COPYLENE-CR350CL-02-Polypropylene-Random-Copolymer-Clarified.php

| Physical Properties | Metric | English | Comments |
|---------------------|---|---|------------|
| Density | 0.902 g/cc | 0.0326 lb/in ³ | ASTM D792 |
| Melt Flow | 35 g/10 min @Load 2.16 kg, Temperature 230 °C | 35 g/10 min @Load 4.76 lb, Temperature 446 °F | ASTM D1238 |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|------------|---------------|---|
| Tensile Strength, Yield | 27.6 MPa | 4000 psi | (2 in/min); ASTM D638 |
| Elongation at Yield | 13.6 % | 13.6 % | ASTM D638 |
| Flexural Modulus | 1.00 GPa | 145 ksi | 0.05 in/mm, 1% Secant, Procedure A; ASTM D790 |
| Izod Impact, Notched | 0.694 J/cm | 1.30 ft-lb/in | Method A; ASTM D256 |

| Thermal Properties | Metric | English | Comments |
|---|---------|---------|-----------------------|
| Deflection Temperature at 0.46 MPa (66 psi) | 76.5 °C | 170 °F | Unannealed; ASTM D648 |

| Descriptive Properties | Value | Comments |
|------------------------|-------------------|---------------------------------|
| Process | Injection Molding | |
| Region | Mexico | Bamberger Polymers Distribution |
| | US & Canada | Bamberger Polymers Distribution |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China